

JF-11747

PVC Flooring Print Layer Film

Description: Single-ply unsupported calendered film, 16 mil (0.41 mm).

Typical Applications: Flooring Print Layer

Typical Processes Supported: Heat Lamination

Property		Typical Results	Units	Test Method
Elongation	MD	>300	%	ASTM D882
	CD	>300		
Tensile Strength	MD	>3400	psi	ASTM D882
	CD	>3400		
100% Modulus	MD	>2500	psi	ASTM D882
	CD	>2500		
10% Modulus	MD	>2400	psi	ASTM D882
	CD	>2400		
Thickness		Target \pm 0.001	Inches	SAE J882
Hardness		55 \pm 5	Shore D	ASTM D2240
Specific Gravity		1.32 \pm 0.02	SG	ASTM D792
Dimensional Stability		<2.5	%	10 m @ 100°C
Embossing		Pass	NA	Visual, to master

The above properties do not constitute a warranty or specification. Test values are based on material conditioned and tested in a controlled laboratory environment using established standards and procedures. Properties may vary based on embossed grain, color, multi-ply laminate construction and other variables.

O'SULLIVAN FILMS, INC.
1944 Valley Avenue
Winchester, Virginia 22601
Tel. 540-667-6666
Fax. 540-722-2695
www.osul.com